TOP-air GRP antislip



PRODUCT DESCRIPTION

Top layer: GRP anti-slip coating (sanded) similar to RAL 7030*

Core: PP-honeycomb

Bottom layer: GRP woven roving, white

*other colours on request



Lightweight panel made of high-strength honeycomb core, a woven glass roving reinforced lower facing sheet as well as a non-slip and wear-resistant GRP top layer.

PROPERTIES

- non-slip and wear-resistant top layer
- high stiffness and light weight
- abrasion resistance better than plywood according to DIN 53754
- excellent energy absorption

- moisture resistant
- large dimensions in one piece possible
- thickness 17 65 mm, length up to 6000 mm

DIMENSIONS

Format	Length [mm]	Width [mm]	Thickness [mm]
Standard			31
Special dimensions*	max. 6000	max. 2900	max. 65
Talaranasa	Langth [mm]	Width [mm]	Thiskness [mm]

Tolerances	Length [mm]	Width [mm]	Thickness [mm]
Cut to size	+2/-2	+1/-2	+0/-1

^{*}on request

TOP-air GRP antislip



GENERAL PHYSICAL PROPERTIES

Service temperature	Abrasion resistance acc. 5131 Abraser, H18	Anti slip characteristic acc. DIN51131	
[°C]	[mg/100U]		
-30 to +80	42,6	R13	

MECHANICAL PROPERTIES

Thickness	Weight per unit area	Thermal insulation U-value	Modulus of elasticity	Bending strength	Bending stiffness
[mm]	[kg/m²]	[W/m²K]	[N/mm²]*	[N/mm²]**	[Nm²]***
31	7,8	2,26	1.830	16	4543

^{*}valid for support distance of 800 mm

All these specifications are based on our most-up-to-date information but are subject to changes at any time. A legally binding assurance of certain properties or the suitability of an individual type for a specific field of application cannot be assumed from these specifications. All information is provided without any obligation. No legal liability can be assumed.

^{**}values determined with three-point-bending test acc. to ISO 178: test sample width 80 mm/support distance 250 mm

^{***}valid per 1 m panel width